







**PRODUCT DATA SHEET
TPE 65AB**

Property	Test Method	Test Unit	Typical Value
Hardness, 5 second	TPE-0169 (ASTM D 2240)	Shore A	65
Specific gravity	TPE-0105 (ASTM D 792)		.98
Tensile strength, ultimate	TPE-0153 (ASTM D 412)	MPa (psi)	4.8 (695)
Elongation, ultimate	TPE-0153 (ASTM D 412)	percent	250

SEE BELOW FOR RUBBER SHAPES AND SIZES

	B-150 =	$\frac{7}{16}$ "
	B-140 =	$\frac{5}{16}$ "
	B-109 =	$\frac{3}{16}$ "
	W-513 =	$\frac{1}{8}$ "
	W-516 =	$\frac{5}{16}$ "
	W-520 =	$\frac{7}{16}$ "

SEE SHEET A1 OF SHOP DRAWINGS FOR RUBBER ALLOCATIONS AND QUANTITIES